

Flexible Reinforcements

Limited

Bancroft Road,
Burnley, Lancashire, BB10 2TP, England
Tel : 44 (0) 1282 478222 Fax : 44 (0) 1282 478210

DOC REF: QA40	B17	ISSUE DATE: 01/01/2007	ISSUE NO: 3	AUTHORISED BY:
---------------	-----	------------------------	-------------	----------------

WAVESPAN 20T 660 GSM 210 DENIER FR

	METHOD OF TEST TO BS 3424
WEIGHT 660 +/- 7.5%	PART 3, METHOD 5A
BURST STRENGTH (kN/msq) 965 MIN	PART 6, METHOD 8B
BREAKING LOAD (N/5cm) L 300 MIN	PART 4, METHOD 6
BREAKING LOAD (N/5CM) T 400 MIN	PART 5, METHOD 7B
TONGUE TEAR (N) L 175 MIN	PART 9, METHOD 11B
TONGUE TEAR (N) T 80 MIN	PART 8, METHOD 10A
RESISTANCE TO FLEX CRACKING (CYCLES)	
COLD CRACK (C) -4 MAX	
FLAME RESISTANCE TO COMPLIE TO	BS5867:PART 2:1980:TYPE B

CONTACT SALES OR TECHNICAL DEPARTMENT IN CASE OF ANY QUERIES

SPECIAL PROPERTIES FORMULATED TO CONFORM TO THE FLAMMABILITY AND TOXICITY REQUIREMENTS OF BS 5665:PART 2:1989 AND PART 3 :1989 WHICH IS EQUIVALENT TO EN71 PART 2 & PART 3 :1988

2 x 250MYM GLASS CLEAR, UV STABILISED, FLAME RETARDANT, PVC FILMS LAMINATED TOGETHER WITH 210 DENIER HIGH TENACITY NYLON YARN AT 15 THREADS/INCH

A Member of the Tellar Holdings Group
Registered Office:
The Copper Room, Deva Centre, Trinity Way, Manchester M3 7BG
Registered in England 876491



Flexible Reinforcements

Limited

Bancroft Road,
Burnley, Lancashire, BB10 2TP, England
Tel : 44 (0) 1282 478222 Fax : 44 (0) 1282 478210

DOC REF: QA40	<input type="text" value="B18"/>	ISSUE DATE: <input type="text" value="14/12/1998"/>	ISSUE NO: <input type="text" value="2"/>	AUTHORISED BY: <input type="text"/>
---------------	----------------------------------	---	--	-------------------------------------

WAVESPAN 35 610 GSM 210 DENIER

		METHOD OF TEST TO BS 3424
WEIGHT	<input type="text" value="610 +/- 7.5%"/>	<input type="text" value="PART 3, METHOD 5A"/>
BURST STRENGTH (kN/msq)	<input type="text" value="800 MIN"/>	<input type="text" value="PART 6, METHOD 8B"/>
BREAKING LOAD (N/5cm) L	<input type="text" value="300 MIN"/>	<input type="text" value="PART 4, METHOD 6"/>
BREAKING LOAD (N/5CM) T	<input type="text" value="380 MIN"/>	
TONGUE TEAR (N) L	<input type="text" value="175 MIN"/>	<input type="text" value="PART 5, METHOD 7B"/>
TONGUE TEAR (N) T	<input type="text" value="80 MIN"/>	
RESISTANCE TO FLEX CRACKING (CYCLES)	<input type="text"/>	<input type="text" value="PART 9, METHOD 11B"/>
COLD CRACK (C)	<input type="text" value="-30 MAX"/>	<input type="text" value="PART 8, METHOD 10A"/>
FLAME RESISTANCE	<input type="text" value="NO"/>	<input type="text"/>

CONTACT SALES OR TECHNICAL DEPARTMENT IN CASE OF ANY QUERIES

SPECIAL PROPERTIES FOR USE IN COLD STORES.

2 x 250MYM GLASS CLEAR, UV STABILISED, LOW TEMPERATURE, PVC FILMS LAMINATED TOGETHER WITH 210 DENIER HIGH TENACITY NYLON YARN AT 15 THREADS/INCH

A Member of the Tellar Holdings Group
Registered Office:
The Copper Room, Deva Centre, Trinity Way, Manchester M3 7BG
Registered in England 876491

